

## EFFISUS BONDING KFP ADHESIVE

### DESCRIPTION

Effisus Bonding KFP Adhesive is used for bonding EPDM and butyl to concrete, masonry, wood, glass, aluminium, steel and bitumen or for lap joint connections.

### TECHNICAL DATA

Technical characteristics	
Base	Styrene rubber, containing solvents
Colour	Black
Viscosity	Pasty
Density	1.0 g/cm <sup>3</sup>
Solid content	Approx. 75%
Ventilation time	Approx. 30 sec
Open time	Approx. 10 min
Consumption	Approx. 200-300 g/m <sup>2</sup>

### OTHERS

#### Processing temperature

-5°C to +35°C (surface temperature)

#### Preparation

The surfaces must be dry, clean and free of dust and grease. Pretreatment may be recommended.

Effisus Bonding KFP Adhesive can be apply with hand or air gun or using a spatula.

Insert the EPDM or butyl material to adhere/ seal immediately, after 10 minutes at the latest and press.

The exact waiting time depends on room temperature, film thickness and absorbency of the substrate.

Due to the different compositions and qualities of foils, preliminary tests are recommended.

#### Cleaning

Effisus Setup PR Cleaner.

#### Storage

Store in original containers, at temperatures between +15°C and +35°C and not for more than 24 months.

#### Safety

Please notice the indications on safety-data-sheet and the safety-indications on the labels of each product for the treatment of our products. Especially the directions of the Dangerous Substance Regulation have to be respected.

Keep the safety-data-sheet of the product you treat ready to hand. It gives you valuable indications for the safe usage, disposal and in case of accidents.

#### Packaging

600ml Sachets (Carton of 12 units).

#### Accompanying Document

Edition 02/2012

#### Version

V 1.1 . AP . 14/07/2014 1/1