

## EFFISUS PRIMER 9800

### DESCRIPTION

Effisus Primer 9800 is a polymer based primer for consequente use with self-adhesive Effisus Alltitegutter membrane, and for priming porous substrates.

### TECHNICAL DATA

Typical Physical Properties and Characteristics	
<b>Base</b>	Primer based on a synthetic rubber and synthetic resins, dissolved in inflammable organic solvents.
<b>Colour</b>	Black
<b>Volume</b>	5 l/un
<b>Weight</b>	4,2kg/un
<b>Viscosity (20°C)</b>	900 ± 100 Pa.s
<b>Flash point</b>	< 0°C
<b>Solids</b>	36,3%
<b>Density (20°C)</b>	840 ± 10 kg/m <sup>3</sup>
<b>Coverage rate</b>	125-250g/m <sup>2</sup> depending on substrate
<b>Application temperature</b>	> +5°C Effisus recommends preheating the adhesive when applying at temperatures between 5°C and 15°C, to improve efficiency.

### APPLICATION

- Effisus Primer 9800 is ready-for-use and must not be thinned or mixed with other products.
- The material and the substrate to be glued must be dry and clean.
- Effisus Primer 9800 should be applied in a thin even layer with a stiff brush or roller. Before unrolling the membrane, check that the primer is totally flashed off.
- Maximum open time is 3 hours. Effisus Primer 9800 may only be used in dry weather conditions, no moisture shall be enclosed between the primer layer and the self-adhesive membrane. When Effisus Primer 9800 was exposed to precipitation, moisture, and dirt, a new layer shall be applied.

## OTHERS

### Advantages

Dust and loose particles are bonded  
Increase the adhesion and water-resistance of the bond  
Decrease the minimum process temperature  
Quick drying of the primer layer.

### Suitable substrates

Concrete, wood, metal or insulation with facing intended for bonding (check technical data sheet insulation).

### Limitations

It is not suitable as a primer for EPS, XPS and plasticized PVC foil.

### Cleaning

Equipment and tools can be cleaned with Effisus Cleaner or similar, immediately after use.

### Storage and Shelf Life

Store material in original unopened containers in a well ventilated place.  
Shelf life is 12 months when stored in an unopened container.

### Safety

Prior to working with this product consult product label and Safety Data Sheet (SDS) for necessary health and safety precautions. Effisus Primer 9800 is highly flammable. Keep away from open fire.

### Version

V 1.3 – MD – 11/07/2022